

# CCREFRACTORIES TECHNICAL DATA SHEET

**CHROME-ALUMINA BRICK (CRAL-80)** 

#### **ENGINEERED FOR EXTREME EROSION RESISTANCE & CORROSIVE ENVIRONMENTS**

#### IN NON-FERROUS AND PETROCHEMICAL OPERATIONS

The Chrome-Alumina Brick (CRAL-80) is a premium-quality, high-density refractory brick made with high-purity alumina and fused chromia. This brick is designed to offer outstanding resistance to corrosive slags, vapours, and high mechanical wear in intense thermal environments. The CRAL-80 performs exceptionally well in non-ferrous smelters, slag cleaning units, and coal chemical applications, where chemical attack and structural erosion are common failure modes.

TECHNICAL SPECIFICATIONS	
PROPERTY	CRAL-80
Cr <sub>2</sub> O <sub>3</sub> (Chromia)	≥ 18%
Al <sub>2</sub> O <sub>3</sub> (Alumina)	≥ 75%
Fe <sub>2</sub> O <sub>3</sub> (Iron Oxide)	≤ 0.8%
Apparent Porosity	≤ 17%
Bulk Density	≥ 3.20 g/cm³
Cold Crushing Strength (CCS)	≥ 90 MPa
Refractoriness Under Load	≥ 1700 °C @ 0.2 MPa
Thermal Conductivity (1000°C)	4.5–5.2 W/m⋅K

#### **TYPICAL APPLICATIONS**

- Flash Smelters & Converters –
   Non-ferrous metallurgy
- Slag Cleaning Furnaces Lead, copper, and nickel operations
- Gasifiers and Reactors Petro chemical and coal chemical units
- Tapping Channels & Launders –
   Handling of aggressive molten slags
- Shaft Kilns & Chimneys Where acidic vapours are present

## PERFORMANCE CHARACTERISTICS

### **INSTALLATION & HANDLING**

- Can be installed using chromia-compatible mortars where required.
- Store bricks in a dry, ventilated warehouse and avoid direct moisture exposure.
- Use protective handling practices to avoid chipping or breakage.

# **QUALITY & COMPLIANCE**

- Produced under ISO 9001:2015 certified facilities.
- Material batches are tested for dimensional tolerances, physical strength, and compositional accuracy.
- Custom grades available on request to match specific operating conditions.
- Superior Chemical Resistance: Resists attack from chromite-rich slags and aggressive vapours.
- High Mechanical Strength:
   Maintains structural integrity in high-pressure applications.
- Thermal Stability: Withstands rapid heating and cooling cycles.
- Low Porosity: Enhances erosion resistance and prevents slag penetration.
- Extended Campaign Life: Ideal for critical process zones with minimal replacement needs.



www.dgc-africa.com REACH OUT TO US contactus@dgc-africa.com

